



## TECHNICAL DATA SHEET

### EBA 1522 - 60

#### I. DESCRIPTION

EBA 1522 - 60 is a styrenated alkyd based on mixed oil with superior in drying time and excellent hardness. It can be used for air-drying enamels for metals and hammerstone finishes.

#### II. PERFORMANCE

- Fast dry.
- Good hardness & mechanical properties.
- Good gloss and gloss retention.
- Good chemical resistance.

#### III. SUGGESTED USES

- Air-drying enamels for metals.
- Hammerstone finishes.

#### IV. SPECIFICATION

- Non-Volatile (150 °C, 15 mins) : 60 ± 1 %
- Viscosity (25 °C, Gardner-Holdt) : Z1 - Z4
- Acid Value (mg KOH/g solid) : maximum 10
- Color (Gardner-Holdt) : maximum 10
- Appearance : clear & clean
- Specific Gravity (25 °C) : ca. 0.988

#### V. STANDARD PACKING

200 kgs in metal drums.

#### VI. STORAGE AND HANDLING

- Store in proper warehouse.
- Keep container closed when not in use.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.