



## TECHNICAL DATA SHEET

### EBL - 3426 P

#### I. DESCRIPTION

EBL - 3426 P is finely divided particles and of medium viscosity.

#### II. PERFORMANCE

- Clear.
- Glossy.
- Good water resistance.

#### III. SPECIFICATION

- Non-Volatile (150 °C, 15 mins) : 50 ± 1 %
- Viscosity at 30 °C, cPs : 4,000 - 6,000  
(Brookfield RVT, No.5/50 rpm)
- pH value : 8.0 - 9.0
- Appearance : Milky White
- Density, (30 °C), gr/cm<sup>3</sup> : 1.03 - 1.08
- Particle size, Mastersizer/E micron : 0.20 - 0.30
- Theoretical Tg, °C : + 8
- Type dispersion : Anionic
- Resistance to frost, °C : Down to ca. 0

#### IV. STANDARD PACKING

200 kgs in open head metal drums packed inside with 2 liners of HDPE plastic bags.

#### V. STORAGE

- Avoid direct sunlight.
- Keep the plastic bags for remaining stock tightly sealed to avoid skinning.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.



## TECHNICAL DATA SHEET

---

- Kept in tightly closed containers in a cool but frost-free place.
- Storage life is 6 months after delivery .

---

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

---

PT. ETERNAL BUANA CHEMICAL INDUSTRIES  
Tel. (62-21) 571 2998, Fax : (61-21) 571 2678

Issue date : Jan 10, 1996  
Revised no : 01  
Revised date : June 01, 2001