



## TECHNICAL DATA SHEET

### EBP - 2415

#### I. DESCRIPTION

EBP - 2415 is a medium reactive, pre-promoted unsaturated polyester resin specially designed for casting products.

#### II. PERFORMANCE

- Flexible and crack resistance.
- High solid contents.
- Good transparency.
- Offers compatibility with fillers.
- Has proper rate of through hardening.

#### III. SUGGESTED USES

- For the manufacture of casting products.

#### IV. SPECIFICATION

- Non-Volatile (105 °C, 3 hours) : 58 - 62 %
- Viscosity at 25 °C, cPs : 160 - 260  
(Brookfield LVT, No.2/60 rpm)
- Acid Value : maximum 30 mg KOH/g
- Color : bluish - greenish
- Appearance : clean/clear
- Gelling time at 25 °C (1 % MEKPO 50 %) : 4 - 8 minutes

#### V. STANDARD PACKING

230 kgs in metal drum.

#### VI. STORAGE

- Storage life decreases with increasing temperature.
- Avoid exposure to heat source such as direct sunlight or steam pipes.
- Keep containers sealed to prevent moisture pick up and monomer loss.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

PT. ETERNAL BUANA CHEMICAL INDUSTRIES  
Phone (62-21) 571 2998, Fax (62- 21) 571 2678

Issue Date : August, 10, 2001  
Revised no : 1  
Revised date : September 11, 2009